

EVO-STIK 8000

SOLVENTED CONTACT ADHESIVE

EVO-STIK 8000 is a good quality general purpose neoprene adhesive, it can be used as either a single or two part adhesive depending on the materials to be bonded and the bond strengths required.

RECOMMENDED USE

EVO-STIK 8000 was developed primarily for use with **ACCELERATOR F** to bond a range of rubbers and rubber coated fabrics (e.g. Neoprene, Hypalon, Natural Rubber etc.) in inflatable constructions such as life rafts, dinghies, high speed inflatable boats etc. It may also be used in the manufacture of dry and wet suits for the bonding of rubber or nylon coated fabrics to themselves.

When used with **ACCELERATOR F**, **EVO-STIK 8000** meets the stringent requirements of the Ministry of Defence Specifications.

EVO-STIK 8000 may also be used as a single component adhesive in many general purpose applications for bonding materials such as Formica, Melamine and PVC laminates to wood metal etc. It may also be used to bond PVC to metal, wood etc., but it must be used with accelerator. It is not recommended for bonding plasticised PVC or expanded polystyrene.

BONDING INSTRUCTIONS

SURFACE PREPARATION

- Substrates to be bonded should be perfectly clean dry and free from dust, grease and other contaminants.
- **INFLATABLES**
 - Neoprene, Natural Rubber and Hypalon coated materials should be lightly buffed and solvent wiped to attain maximum results
- **WET & DRY SUITS**
 - For best results all surfaces should be cleaned with a solvent wipe using **EVO-STIK CLEANER 1** or **SATREAT**.

APPLICATION

- **MIXING RATIO**
 - **EVO-STIK 8000** 100 parts by weight
 - **ACCELERATOR F** 5 parts by weight
 - Material should be mixed thoroughly, this will take 3 - 4 minutes of mixing by hand or 1 minute using a mechanically stirrer.
- **DRY / WET SUITS**
 - Apply one coat of adhesive to each surface and allow to dry for 10 - 20 minutes to ensure complete solvent evaporation.
 - Apply a second coat to each surface and allow to dry for 10 - 20 minutes until solvent has evaporated but adhesive remains tacky
 - Bring the two surfaces together and apply pressure by hand roller or pinching.
 - Full cure can take up to 3 days but good handling strength will be obtained immediately.

This Product Data Sheet covers just one of a large range of products supplied by Bostik Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

- **INFLATABLES**
 - A minimum of two coats should be applied to each surface.
- **GENERAL SINGLE COMPONENT**
 - Apply an even coat of adhesive to both surfaces to be bonded, allow to dry for 10 - 20 minutes to allow the solvent to evaporate but the adhesive remains tacky
 - Bring both surfaces together and consolidate the bond by roller or press.

TYPICAL CHARACTERISTICS

	EVO-STIK 8000	ACCELERATOR F
Physical Form:	Liquid	Liquid
Colour:	Light straw	Pale brown
Chemical Type:	Polychloroprene rubber, synthetic resin blend	Polyisocyanate
Solvent:	Mixture of hydrocarbons and Ketone	Ethyl Acetate
Viscosity (Brookfield RVT, 10rpm at 20°C):	Approx. 2400 mPas	
Solids Content:	Approx. 22%	Approx. 27%
Specific Gravity:	Approx. 0.87	Approx. 0.98
Flammability:	Highly flammable	Highly flammable
Open Time:	10 - 30 minutes subject to substrate conditions & length of time after addition of accelerator	
Pot Life (2 component mix):	Approx. 4 hours	

PACKAGING

For current pack sizes please contact the customer service department

STORAGE

Store in accordance with the requirements of the petroleum regulations in a dry flameproof area between 5 and 25°C.

SHELF LIFE

EVO-STIK 8000 - 12 months stored in its original container under the above conditions.

ACCELERATOR F - 6 months stored in its original container under the above conditions.

MATERIAL SAFETY DATA

For further information refer to the relevant Health and Safety Data Sheet.

This Product Data Sheet covers just one of a large range of products supplied by Bostik Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

Bostik Limited, Ulverscroft Road, Leicester, LE4 6BW England. Tel: +44 (0)1785 272727 Fax: +44 (0)116 253 1943

www.Bostik.co.uk